

## **Pengaruh Konsentrasi Alkali pada Perendaman Serat terhadap Kekuatan *Bending* dan *Impact* Komposit Serat Rami Bermatrik *Polyester***

### **Abstrak**

Tujuan dari penelitian ini adalah untuk mengetahui kekuatan *bending* dan *impact* yang paling tinggi dari komposit berpenguat serat rami bermatrik *Polyester* dengan variasi konsentrasi perendaman alkali pada serat 0%, 2,5%, 5%, 7,5%, 10% selama 2 jam. Setelah itu dilakukan pengambilan foto makro pada spesimen yang memiliki kekuatan *bending* dan *impact* paling tinggi untuk mengetahui kegagalan komposit.

Pada penelitian ini bahan yang digunakan adalah resin *Polyester* 108 dan serat rami yang disusun secara acak dengan fraksi volume 15%. Komposit dibuat dengan metode cetak tekan. Pengujian yang dilakukan adalah pengujian *bending* dengan menggunakan standar ASTM D 790-03 dan pengujian *impact* metode *charpy* dengan menggunakan standar ASTM D 256-00.

Hasil pengujian *bending* yang paling tinggi adalah pada konsentrasi alkali 2,5% sebesar 61,781 MPa dan pengujian *impact* yang paling tinggi adalah pada konsentrasi alkali 0% sebesar 0,0130 J/mm<sup>2</sup>. Berdasarkan pengamatan struktur makro didapatkan jenis kegagalan *fiber pull out* dan *fiber break* pada komposit.

**Kata kunci:** serat rami, *Polyester* 108, perendaman alkali, *bending*, *impact*

## ***The Effects of Alkali Concentration on Fibers Soaking on The Bending Strength and Impact of Composite Polyester Hemp Fiber***

### ***Abstract***

*The purpose of this study was to identify the highest bending strength and impact of polyester reinforced hemp fiber reinforced composites with changes in alkaline immersion concentration in the fibers 0%, 2.5% , 5%, 7.5%, 10% for 2 hours. After that, a macro photograph is taken of the sample that has the highest bending strength and impact to determine the composite failure.*

*In this research, the materials used were polyester resin 108 and hemp fibers randomly arranged with a volume fraction of 15%. The composites were manufactured by the press mold method. The tests performed were bending tests using ASTM D 790-03 and test the impact of the charpy method using ASTM D 256-00.*

*The highest bending test result was obtained with an alkaline concentration of 2.5% at 61.781 MPa and the highest impact test is at a 0% alkali concentration of 0.0130 J / mm<sup>2</sup>. Based on the observation of the macro structure, there were a type of fiber pull out and fiber break on the composite.*

***Keywords:*** fiber hemp, polyester 108, alkaline soak, bending, impact